



CLEANING

WS: Water/Solvent Cleaner - Spot clean with a mild solvent, an upholstery shampoo, or the foam from a mild detergent. When using a solvent or dry cleaning product, follow instructions carefully and clean only in a well-ventilated room. Avoid any product that contains carbon tetrachloride or other toxic materials. With either method, pretest a small area before proceeding. Always rinse promptly with clean water.

CFC: Coated Fabrics Cleaning - When a spill/stain occurs wipe immediately with a clean dry cloth. Carefully remove the majority of the stain then follow the steps below.

Soap & Water - Remove ordinary dirt and smudges with a mild soap and water solution using a soft cloth or towel. Rinse with fresh water and wipe dry.

Non-abrasive Cleaners - If residue remains, use a straight application of the following cleaners: Fantastik or 409 and gently clean with a soft cloth. Rinse with fresh water and wipe dry.

Isopropyl Alcohol - More stubborn stains may be eliminated using a cotton cloth soaked in 70-91% isopropyl (rubbing) alcohol. Wipe without spreading stain to surrounding area. A second application should be applied with vigorous rubbing in a circular motion. For highly textured material, a soft brush is recommended to clean valleys and crevices. Rinse with fresh water and wipe dry.

BC: Bleach Cleanable - 1 parts bleach, 9 parts water = 10% bleach, 90% water solution. Do not clean / disinfect fabric for longer than 10 minutes using the 10% bleach solution. Always rinse promptly with clean water after applying the bleach solution. Failure to do so will void any and all warranties.

Additional cleaning details at www.mayerfabrics.com

CATEGORY

Upholstery

PROPERTIES



CONTENT

78% Vinyl - Phthalate Free face, 22% Polyester backing

BACKING

100% Polyester

FINISH

Soil & Stain Resistant Top Coat with Ink Resistant Technology

WIDTH

54"

WEIGHT

30 oz./ln yd

SHOWN RAILROADED

No

DIRECTIONAL

No

ROLL LENGTH

30 yards

BREAKING STRENGTH

Warp 167/Fill 97

ABRASION RESISTANCE

Exceeds 1,000,000 Double Rubs (Wyzenbeek) Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

COLORFASTNESS TO CROCKING

Dry: Class 4 min/Wet: Class 4 min

COLORFASTNESS TO LIGHT

650 hours

APPLICATION

Atrium, Indoor, Marine Use, Outdoor

FLAMMABILITY

Passes Cal TB 117-2013; NFPA 260/UFAC Class 1; AB 2998 Compliant; BIFMA; Boston Fire Dept. Code (BFD IX-1); FAA/FAR 25.853(a) & Appendix F Part I(a)(11); Fed. Spec. CID A-A-2950/supersedes CCC-A-680A; FMVSS 302; NY/NJ Port Authority

WARRANTY

Standard Upholstery | '5' Five Year Warranty