



CLEANING

CFC: Coated Fabrics Cleaning - When a spill/stain occurs wipe immediately with a clean dry cloth. Carefully remove the majority of the stain then follow the steps below.

Soap & Water - Remove ordinary dirt and smudges with a mild soap and water solution using a soft cloth or towel. Rinse with fresh water and wipe dry.

Non-abrasive Cleaners - If residue remains, use a straight application of the following cleaners: Fantastik or 409 and gently clean with a soft cloth. Rinse with fresh water and wipe dry.

Isopropyl Alcohol - More stubborn stains may be eliminated using a cotton cloth soaked in 70-91% isopropyl (rubbing) alcohol. Wipe without spreading stain to surrounding area. A second application should be applied with vigorous rubbing in a circular motion. For highly textured material, a soft brush is recommended to clean valleys and crevices. Rinse with fresh water and wipe dry.

BC: Bleach Cleanable - 1 parts bleach, 4 parts water = 20% bleach, 80% water solution. Do not clean / disinfect fabric for longer than 10 minutes using the 20% bleach solution. Always rinse promptly with clean water after applying the bleach solution. Failure to do so will void any and all warranties.

Write-Away products from Mayer Fabrics defies unsightly ink spots and paint stains. Take action 'right away' on Write-Away products by following the cleaning instructions for Ink Stains. Always rinse thoroughly with clean water.

Additional cleaning details at www.mayerfabrics.com

CATEGORY
Upholstery

PROPERTIES

CONTENT
45% Polyurethane Polycarbonate - PVC Free face, 55% Polyester backing

BACKING
Polyester

FINISH
WRITE AWAY® - Soil & Stain Resistant Top Coat with Ink Resistant Technology

WIDTH
54"

WEIGHT
20 oz./In yd

SHOWN RAILROADED
No

DIRECTIONAL
Yes

ROLL LENGTH
30 yards

BREAKING STRENGTH
Warp 119/Fill 239

SEAM SLIPPAGE
Warp: 70/Fill: 70

ABRASION RESISTANCE
Passes 250,000 Double Rubs (Wyzenbeek) Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

HYDROLYSIS
10 weeks

COLORFASTNESS TO CROCKING
Dry: Class 4 min/Wet: Class 4 min

COLORFASTNESS TO LIGHT
200 hours

APPLICATION
Indoor

FLAMMABILITY

Passes Cal TB 117-2013; NFPA 260/UFAC Class 1; AB 2998
Compliant

WARRANTY

Standard Upholstery | '5' Five Year Warranty